



### **DESCRIPTION**

Plaster can be cast in water-based paste, for indoor use, without setting. Its texture allows for both manual and mechanical application.

### **RECOMMENDED USES**

Suitable for renewing and coating bottoms and surfaces with irregularities and stipples. On plaster, plaster, cement, concrete, stipple supports, brick, prefabricated block, conventional plastic paint, etc.

### **PROPERTIES**

- . Great strength, hardness and adhesion.
- . Breathable.
- . Good drying.
- . Minimal shrinkage during drying.
- . Penetrating power.
- . Easy to smooth and even.
- . Leveling of supports.
- . No setting.

### **TECHNICAL FEATURES**

Vehicle: Acrylic copolymers in aqueous dispersion.

Pigments: Selected fillers and extenders.

Appearance: Matte.

Diluent: Water.

Solids by weight:  $72 \pm 2\%$

Specific Weight:  $1.82 \pm 0.05$  g/ml

VOC (2010): Maximum 30 g/l

Color: White.

Drying at 20°C: 3 hours.

Sanding at 20 °C: Minimum 16 hours.

Repainting at 20°C: Minimum 24 hours.

Recommended thickness: Apply 3 to 5 mm per coat.

Packaging: 20 kg



### **APPLICATION**

#### **Surface Preparation:**

On new surfaces of building materials, clean the surface to remove dust, grease and dirt in general. The substrate must be completely clean, dry and with a sufficient roughness profile. It is recommended to strengthen the surface or unify the absorption to use an acrylic fixative such as our FIXATIVE to obtain a better result.

On surfaces that have already been painted, remove foreign products that are poorly adhered or in poor condition from the substrate. Open the pore if it is closed, by sanding or other mechanical-manual means. Check the adhesion and treat as on new substrates.

#### **How to use:**

A product to use.

It can be applied with: trowel, air-less gun, spatula and trowel.

Adjust the pressure of the machine between 180-200 Bar. Prime and load the spraying machine and choose the most suitable air-less nozzle. The recommended nozzles for this product are step 6.31 and 6.33 depending on the amount of product to be deposited on the bottom per layer.

Spray the plaster at a distance between 0.7 m and 1.0 m from the substrate, applying it slowly and evenly with the spray gun until a thickness of at least 3 mm per layer is deposited.

Allow the product to absorb well on the bottom and then smooth with the trowel to break up any bubbles that may have formed. If the bubble formation is not too significant, it is not necessary to straighten: let this first layer dry directly. Cross by applying a second coat to get rid of all imperfections.

Never apply below 5°C or above 35°C.

### **REMARKS**

The characteristics of the product are obtained once it has been completely dried and cross-linked, as well as applied to the specified substrates

The actual consumption should be determined for each particular work by means of representative tests.

The data reviewed here are based on our current knowledge, laboratory tests and practical use in specific circumstances through subjective judgments.

Due to the impossibility of establishing an appropriate description for each nature and condition of each surface, it is impossible for us to guarantee total reproducibility in each specific use.

Unless otherwise specifically agreed in writing, both the manufacturer and the seller do not assume any liability arising from the use of our products, for the results, damages, etc., that may arise in applications made in accordance with our recommendations, as these are beyond the control of the company.

### **SHELF LIFE AND SHELF LIFE**

Store the container tightly closed, indoors and at a temperature between 5 and 30°C

The shelf life of the product in its original, unopened packaging is two years.

### **SAFETY & ENVIRONMENT**

No special safety measures are required as it is a water-based product, except for the usual ones. Do not ingest the product. Keep open canisters out of the reach of children. Maintain good ventilation in case of indoor application. For more information, see the product's safety data sheet.

The data indicated in this data sheet may be changed without prior notice.

**REVISION: 04/04/2024**